

AirRepair® Pressurized Cable Leak Sealant

Temperature and Cure Time Chart

Ambient Temperature	Initial Cure Time*
34°F (1°C)	40 Minutes
52°F (11°C)	20 Minutes
70°F (21°C)	10 Minutes
88°F (31°C)	5 Minutes
106°F (41°C)	2.5 Minutes